

NO	ITEM No.	CONSTRUCTION				PROPERTIES			
		COMPOSITION		WIDTH	WEIGH	FINISH	WP	Air Permeability	MVTR
		FACE	BACK	(INCH)	(G/SQM)		(mmHzO)	(cfm)	(gr/m ² /24hr)
1	FT-H6446-5S5	N75% SP25%	P100%	54	245	WR(C6), 3Layer	5K↑	0.4~0.8	7K↑
2	FT-F2100-5S7	N75% PU25%	P100%	54	149	WR(C6), 3Layer	6K↑	0.4~0.8	7K↑
3	FT-F3100-5S7	N82% PU18%	P100%	54	171	WR(C6), 3Layer	7K↑	0.4~0.8	7K↑
4	FT-F3200-5S7	N82% PU18%	P100%	54	183	WR(C6), 3Layer	6K↑	0.4~0.8	7K↑
5	FT-F4100-5S7	N86% PU14%	P100%	54	146	WR(C6), 3Layer	7K↑	0.4~0.8	7K↑
6	FT-F4200-5S7	N86% PU14%	P100%	54	188	WR(C6), 3Layer	6K↑	0.4~0.8	7K↑
7	FT-F5100-5S7	N88% PU12%	P100%	54	186	WR(C6), 3Layer	6K↑	0.4~0.8	7K↑
8	FT-F5200-5S7	N88% PU12%	P100%	54	191	WR(C6), 3Layer	6K↑	0.4~0.8	7K↑
9	FT-Y0201-5S7	P88% PU12%	P100%	54	147	WR(C6), 3Layer	7K↑	0.4~0.8	7K↑
10	FT-Y601R-5S7	N54% P32% PU14%	P100%	54	216	WR(C6), 3Layer	6K↑	0.4~0.8	7K↑
11	FT-H2151-7B5	N100%	P100%	54	224	WR(C6), 3Layer	4K↑	0.4~0.8	7K↑
12	FT-Y7603-1F5	N84% PU16%	P100%	54	321	WR(C6), 3Layer	6K↑	0.4~0.8	7K↑
13	FT-Y0301-1F5	P85% PU15%	P100%	54	309	WR(C6), 3Layer	5K↑	0.4~0.8	7K↑
14	FT-Y3711-5F5	N75% PU25%	P94% PU6%	52	287	WR(C6), 3Layer	4K↑	0.4~0.8	7K↑
15	FT-Y7604-5F5	N88% PU12%	P94% PU6%	54	332	WR(C6), 3Layer	4K↑	0.4~0.8	7K↑
16	FT-Y0311-7B5	N85% PU15%	P100%	54	265	WR(C6), 3Layer	6K↑	0.4~0.8	7K↑

This Technical Data Sheet has the center value and thus it is valid without a signature.

For further products & information, please contact nexture@ftene.com.

Test Methods: WP : ISO 811

AP : ASTM D737

MVTR : JIS L1099-A1

NOTE: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for ensuring that it is suitable for their needs, environment, and end use. Revisions on all data maybe made without notice as Finetex Technology deems appropriate.